Alltimes Intera WB
- Product Information

ALLTIMES COATINGS
EXPERIENCE THE DIFFERENCE IN EVERY COAT



All you need to know:

PRODUCT INFORMATION 1
TECHNICAL INFORMATION 2
COVERAGE GUIDE & APPLICATION 3-4

High-build, low odour, water based system for long-life cladding restoration

What is Alltimes Intera WB?

A high-performance, water-based Acrylated PU coating developed for the refurbishment and protection of internal industrial and commercial environments. Designed for application to internal walls, ceilings, structural steel, galvanised steel and concrete, it delivers a durable, attractive finish with excellent application properties and minimal disruption to occupied buildings.

Its advanced water-based formulation contains very low levels of VOCs, making it an ideal solution where odour needs to be kept to a minimum and solvent-based coatings are unsuitable. The tough semi-gloss finish provides excellent durability whilst maintaining a clean, professional appearance in warehouses, factories, workshops, distribution centres and other commercial premises.

As a single-pack system, Alltimes Intera WB is simple to apply by spray, brush or roller, requiring no complicated mixing. Equipment can be cleaned using water, helping to reduce downtime and improve efficiency on site. Fast drying and easy to apply,

Alltimes Intera WB offers excellent coverage and consistent finish quality, making it suitable for both refurbishment projects and ongoing maintenance programmes.

Why choose Alltimes Intera WB

- ✓ Low odour formulation
- ✓ Very low VOC
- ✓ Water-based technology
- ✓ Excellent coverage
- ✓ Fast drying
- ✓ Spray, brush or roller application
- ✓ Easy water clean-up
- ✓ Durable semi-gloss finish
- ✓ Suitable for occupied buildings

Recommended For

Protection and refurbishment of suitably prepared:

- Internal walls
- Ceilings
- Structural steel
- Galvanised steel
- Concrete
- Other suitably prepared internal surfaces
- Internal cladding

Ideal for:

- Warehouses
- Factories
- Manufacturing facilities
- Workshops
- Plant rooms
- Commercial buildings

Feature:	Result:
Pack Size:	20L Containers (other sizes available on request)
Volume Solids:	At 75 microns DFT the theoretical spread rate is 5.3m^2 to the litre
Coverage:	5.3m^2 per litre, at a DFT of 75 microns.
VOC:	Approximately 20g/litre
Drying Time @ 20°C:	Touch Dry: Approx. 45 minutes
Minimum Application Temperature:	8°C
Appearance When Dry:	Semi-Gloss

Components

- Alltimes Intera WB: 20L Containers

Surface Preparation

- All surfaces should be clean, dry and free from dust, grease, oil and contamination.
- Remove all loose or flaking coatings before application.
- Repair any damaged areas prior to coating.
- Steel surfaces should be clear of rust, cleaned corrosion to ST3 standard and prime accordingly before coating.
- All prepared surfaces must be completely dry before application.

Application of Coating

- Stir thoroughly before use until a consistent, homogeneous product is achieved.
- Apply by brush, roller, airless spray or conventional spray.
- One or two coats may be required depending upon substrate porosity, colour change and desired finish.
- Ideal application temperature is above 8°C.
- Substrate temperature should be at least 3°C above the dew point.
- Relative humidity should not exceed 90%.
- Drying times will be extended in cold or damp conditions.
- Avoid excessive film build as this may increase drying time and affect the final finish.

Airless Spray

- Product supplied ready for use.
- Tip Size: 15 thou
- Tip Pressure: 2,000 to 3,000 psi

Conventional Spray

- Tip Pressure: 40 to 60 psi

Brush & Roller

- Product supplied ready for use

Clean-up

- Clean all equipment immediately after use with clean water
- Do not allow paint to dry inside hoses, guns or spray equipment
- Dispose of surplus product in accordance with local regulations.



Storage

- Store in original unopened containers.
- Store in cool, dry conditions away from direct sunlight.
- Protect from frost.
- Recommended storage temperature: 5°C to 32°C.
- Shelf life approximately 12 months in unopened containers.

Health & Safety

- Please refer to the appropriate Safety Data Sheet before use and follow all relevant health, safety and environmental guidance.

Warranty

When applied in accordance with Alltimes Coatings' published recommendations and specification, Alltimes Intera WB provides a durable protective finish for internal environments. Product performance is dependent upon correct preparation, application and service conditions.

No responsibility can be taken by the manufacturers where conditions of use are beyond our control. All products should be used in accordance with the manufacturer's instructions. For further information please refer to the application guide and Material Safety Data Sheet. This information and guidance is given in good faith and without prejudice and liability, Technical and Safety Data must be observed. All coverages are given as a guide only, as volumes will vary with profile, porosity and method of application. Loss factors should also be taken into account.

ALLTIMES COATINGS
EXPERIENCE THE DIFFERENCE IN EVERY COAT

Alltimes Coatings Ltd.
Unit 17A, Nailsworth Mills Estate,
Nailsworth, Gloucestershire,
GL6 0BS. UK

T: 01453 872 850
E: sales@alltimescoatings.co.uk
W: www.alltimescoatings.co.uk