



Advantage® Metal Primer with Graphene

Unique Graphene enhanced Anti Corrosion primer to coat and protect prepared steel before application of Advantage® Top Coats.



In Liquid Form

Feature	Result
Specific Weight:	1.55 gr/cm ³
Application Temperature:	5°C to +35°C
Volume Solids:	40% typical
VOC:	525g/Lt
Flash Point:	24°C closed cup
Relative Air Humidity:	Maximum 90% R.H.



In Cured Form

Feature	Result
Overcoat Time:	3 Hours (No maximum)
Touch Dry:	1 Hour
Film Dry:	2 Hours
Wet Film Thickness:	190 µm
Dry Film Thickness:	75 µm



General Information

Feature	Result
Shelf Life:	2 years minimum in unopened tins in a cool dry place out of direct sunlight
Coverage:	Theoretical minimum consumption is 4-5m ² per 1L depending on substrate
Pack Sizes:	2.5 Litre & 5 Litre Tins
Colour:	Mid Grey

Ensure Primer is completely dry before applying the top coat.

No responsibility can be taken by the manufacturers where conditions of use are beyond our control. All products should be used in accordance with the manufacturer's instructions. For further information please refer to the application guide and Material Safety Data Sheet. This information and guidance is given in good faith and without prejudice and liability, Technical and Safety Data must be observed. All coverages are given as a guide only, as volumes will vary with profile, porosity and method of application. Loss factors should also be taken into account.

ALLTIMES
COATINGS
EXPERIENCE THE DIFFERENCE IN EVERY COAT

Alltimes Coatings, Units C & D,
Station Road Industrial Estate,
South Woodchester, Stroud,
Gloucestershire. GL5 5EQ. UK

T: 01453 872 850

E: info@alltimescoatings.co.uk

W: www.alltimescoatings.co.uk